

# TILE ADHESIVE PLATINUM PLUS

POLYMER MODIFIED CEMENTITIOUS TILE ADHESIVE **TYPE IV 'T' S2 / C2TES2** FOR VITRIFIED TILES AND NATURAL STONES

## DESCRIPTION

**Tile Platinum Plus** is a high strength, high flexible polymer modified cementitious tile adhesive with enhanced properties of slip resistant, extended open time & excellent bond strength which is necessary for fixing large format tiles/natural stones & slim tiles on vertical & horizontal surface for indoor as well as outdoor application especially in external conditions, high footfall areas & on substrates subject to high deformations/vibrations.

## USES

- All types of ceramic tile, terracotta, pavers, brick, vitrified tiles, glass mosaic tiles, large format tiles, precast terrazzo, marble & natural stones, large thin/ slim tiles, low thickness slabs.

## APPLICATION AREAS

- Floor and wall
- Internal and external areas
- Saunas, spa, fountains & swimming pools etc
- Terraces & balconies, podium decks & facades
- Window/ door frame

## PRODUCT INFORMATION

<b>Chemical base</b>	Portland cement, polymers, selected aggregates and additives
<b>Packaging</b>	20 Kg & 40 Kg
<b>Shelf life</b>	12 months from the date of manufacturing
<b>Storage conditions</b>	Product must be stored in original, unopened and undamaged sealed packaging in dry condition temperature between +5 °C to 35 °C
<b>Appearance</b>	Free flowing grey/white pow
<b>Standard compliance</b>	Type IV 'T'S2 (IS 15477:2019) & C2TES2 (EN 12004:2017)

\*Tensile adhesion strength test after freeze thaw cycles not concluded due to tropical climatic condition.

# TILE ADHESIVE PLATINUM PLUS

## APPLICATION INFORMATION

Mixing ratio	Packing	Water: powder ratio by weight	Quantity of water per bag
	40 Kg grey	0.27-0.29	10.40-12.00 L
	40 Kg white	0.33-0.35	13.20-14.00 L
<b>Fresh mortar density</b>	1.5 – 1.7 Kg/L		
<b>Consumption</b>	Consumption is dependent on the substrate, surface profile, roughness, application technique, tile type, tile size and trowel notch size. (As a guide for a single adhesive layer)		
Size of tiles	Bed thickness	Dry Powder Consumption (Grey)	Dry Powder Consumption (White)
Small	3 mm	2.25 - 2.75 Kg/m <sup>2</sup>	2.25 - 2.75 Kg/m <sup>2</sup>
Medium	4 mm	2.75 – 3.25 Kg/m <sup>2</sup>	2.75 – 3.25 Kg/m <sup>2</sup>
Large	5 mm	3.50 – 4.00 Kg/m <sup>2</sup>	3.50 – 4.00 Kg/m <sup>2</sup>
<b>Coverage</b>			
Pack	Area covered		
20 Kg	5 – 6 m <sup>2</sup> at 3 mm thickness		
<b>Layer thickness</b>	Min 3 mm – Max 12 mm		
<b>Ambient air temperature</b>	+5 °C - +45 °C		
<b>Substrate temperature</b>	+5 °C - +45 °C		
<b>Maturing time</b>	~5 minutes		
<b>Pot life</b>	~120 minutes (100 gm powders at +27 °C)		
<b>Open time</b>	30 – 35 minutes		
<b>Adjustability time</b>	35 – 40 minutes		
<b>Applied product ready for use</b>	Use	Waiting time	
	Grouting Floor/walkable	24 – 36 hours	
	Grouting walls	4 – 6 hours	
	Full traffic	~14 days	
	Water immersion	~21 days	

Values determined at the laboratory conditions: 23 °C ± 2 °C, R.H. 50 % ± 5 %. Higher temperatures will reduce the indicated waiting times, lower temperatures increase them.

Protect from adverse weather conditions, such as extremely high or low (freezing) temperatures, rain, for at least 12-24 hours from application.

# TILE ADHESIVE PLATINUM PLUS

## TECHNICAL INFORMATION

Requirements as per IS 15477:2019 -

TEST PARAMETERS	IS 15477:2019	RESULTS
Tensile Adhesion strength		
Dry condition	$\geq 1.5 \text{ N/mm}^2$	1.6 – 1.8 N/mm <sup>2</sup>
Wet condition	$\geq 1.0 \text{ N/mm}^2$	1.4 – 1.6 N/mm <sup>2</sup>
Shear adhesion strength		
Dry condition	$\geq 1.5 \text{ N/mm}^2$	1.6 – 1.8 N/mm <sup>2</sup>
Wet condition	$\geq 1.0 \text{ N/mm}^2$	1.4 – 1.6 N/mm <sup>2</sup>
Heat ageing	$\geq 1.0 \text{ N/mm}^2$	1.6 – 1.8 N/mm <sup>2</sup>
Transverse deformation (S1)	$\geq 5 \text{ mm}$	$\leq 5 \text{ mm}$
Slip	$\leq 0.5 \text{ mm}$	$\leq 0.3 \text{ mm}$

Requirements as per EN 12004:2017 -

TEST PARAMETERS	EN 12004:2017	RESULTS
Tensile Adhesion strength		
Dry condition	$\geq 1.0 \text{ N/mm}^2$	1.6 – 1.8 N/mm <sup>2</sup>
Wet condition	$\geq 1.0 \text{ N/mm}^2$	1.4 – 1.6 N/mm <sup>2</sup>
Heat ageing	$\geq 1.0 \text{ N/mm}^2$	1.6 – 1.8 N/mm <sup>2</sup>
Extended open time, Tensile adhesion strength	$\geq 0.5 \text{ N/mm}^2$ after not less than 30 minutes	1 – 1.2 N/mm <sup>2</sup>
Transverse deformation (S1)	$\geq 5 \text{ mm}$	$\leq 5 \text{ mm}$
Slip	$\leq 0.5 \text{ mm}$	$\leq 0.3 \text{ mm}$

\*Values determined at the laboratory conditions: 23 °C ± 2 °C, R.H. 50 % ± 5 %, results may vary based on site conditions, contact Kansai Nerolac Paints technical team for assistance.

## APPLICATION PROCESS

### SUBSTRATE PREPARATION

- The substrate must be levelled, cured, undamaged, compact, rigid and free from any deleterious material.
- Dampen the dry surface with water and excess water should be washed off.
- New concrete substrate should be 28 days old before application which will reduce linear shrinkage from tile fixing surface.
- Smooth surfaces should be roughened lightly to improve adhesion.
- Expansion joints to be provided and filled with suitable sealant.
- For applications in hot climate or on absorbent substrates, thoroughly pre-dampen the surface immediately prior to product application. Avoid any ponding/standing water on the surface. Surface must not be damp to touch.

- If waterproofing layer required, cement based, and acrylic based waterproofing products from Nerolac Perma range must be applied to the substrate before tiling.

### MIXING

- Pour the recommended amount of clean cold water into a suitable, clean mixing container.
- Slowly add Tile Gold powder to the water and then mix thoroughly using a low speed (<500 rpm) drill mixer until the material is fully mixed and lump free. Avoid entraining air into the mix by over mixing.
- Allow the product to mature 4-5 minutes before remixing for 30 seconds.
- The finished mix has a creamy consistency, uniformly coloured and is easy to apply and spread.

# TILE ADHESIVE PLATINUM PLUS

## APPLICATION

- Tile Platinum Plus is applied using a suitable notch trowel. Apply adhesive on a prepared fixing surface with trowel and comb to the required bed thickness. Coverage on the back of the tile should be 100%.
- Tiling must be carried out on freshly applied adhesive, exerting adequate pressure to ensure complete and uniform contact with the adhesive for optimum bond.
- Check the adhesive ribs periodically, if the skin has formed, remove the dried adhesive and apply fresh adhesive.
- Press the tiles firmly into position, checking periodically that good contact is maintained with the back of each tile and beat it using rubber mallet to imbed tile and just level.
- Adjust the tile if required.
- Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.
- After the required waiting time apply the appropriate grout into the tile joints.
- For tiles  $>900 \text{ cm}^2$  (30x30 cm), the double spreading (buttering technique) is always recommended.
- On cementitious substrates Tile Platinum Plus can be used for laying non-absorbent tiles on non-heated floors in outdoor and indoor applications up to 32 ft<sup>2</sup> (e.g. 4 ft x 8 ft). On walls indoor up to 8 ft height up to 32 ft<sup>2</sup> (e.g. 4 ft x 8 ft) and outdoor up to 20 ft height up to 8 ft<sup>2</sup> (e.g. 2 ft x 4 ft).

## Other Products Categories available

Nerolac Perma brings you the wide range of constructive solution



WATERPROOFING



REPAIR  
REFURBISHMENT



CONCRETE



BUILDING  
FINISHES



FLOORING



SEALING &  
BONDING



TILE  
SETTING



**KANSAI NEROLAC PAINTS LIMITED**  
28TH FLOOR, A WING, MARATHON FUTUREX, N. M. JOSHI  
MARG, LOWER PAREL, MUMBAI 400013, MAHARASHTRA  
FOR CONSUMER COMPLAINTS, PLEASE WRITE TO  
MANAGER, CONSUMER CARE CELL AT REGD. OFFICE  
ADDRESS OF THE MARKETER I.E. KANSAI NEROLAC PAINTS  
LIMITED OR CALL 18002092092 (TOLL FREE) OR EMAIL:  
COMPLAINTS@NEROLAC.CO

## Disclaimer:

The product information and application details given by the company has been provided in good faith and is meant to serve only as a general guideline during usage. The performance claims made are based on the tests carried out under controlled conditions and our experience with the type of products, therefore actual performance will depend on local factors prevailing at that point of time. Users are advised to carry-out sample tests by taking trials to ensure the suitability of products for their requirement, prior to full-scale usage of our products. The Company is not liable for factors beyond its control such as application during adverse climatic conditions, use of improper application tools/techniques and surface preparation, any structural defects or the inferior quality of materials other than paints. The warranty/guarantee clauses shall accordingly be amended.