



ENAMEL

NEROLAC SATIN ENAMEL

SMOOTH FINISH

PRODUCT DESCRIPTION

Nerolac Satin Enamel is specially formulated to give an excellent smooth finish, resembling the smoothness of Satin to masonry, wood and metal surfaces. It can be easily cleaned to give a new look to the surface.

PERFORMANCE FEATURES & BENEFITS

- Very smooth Satin like appearance.
- Good washability.
- Very good flow and brushability.
- Hard durable film.

RECOMMENDED USAGE

It is specially recommended for all suitably primed masonry, wooden and metal surfaces.

SURFACE PREPARATION

Ensure the surface is clean, dry and free from all defective or poorly adhering material, dirt, grease, wax etc. Remove all loose or poorly adhering materials by rubbing down, using a suitable abrasive paper and thereafter wipe off. Treat fungus affected area using Nerolac Fungicidal Solution. Allow to react for 6 - 8 hrs. Apply a coat of suitable Primer followed by Putty (if required) to level the dents and make the surface uniform. Apply a coat of Primer again. Then apply two coats of Nerolac Satin Enamel.

RECOMMENDED SYSTEM FOR APPLICATION

For Masonry Surfaces



For Metal Surfaces



For Wooden Surfaces



Sand the surface with Emery Paper and wipe clean before application of subsequent coats.

* Nerolac Cement Primer (Solvent Thinnable) or Goody Universal Primer (Solvent Thinnable).

° Nerolac Red Oxide Metal Primer / Goody Red Oxide Metal Primer / Nerolac Syn. Primer Surfacer and Brushing Filler.

• Nerolac Wood Primer, White or Pink.

Air dry min. 8 hrs. for dry scuff & min. 16 - 18 hrs. for wet scuff. In case of stoving, give flash off 30 minutes. Stoving schedule is 30 minutes at 100°C.

For hassle free painting dial 1800 22 0024 or SMS 'NEROLAC' to 4646.



Nerolac House, Ganpatrao Kadam Marg, Lower Parel, Mumbai 400013.

TECHNICAL DATA

Coverage**	150 -170 sq. ft. / ltr. / coat., when applied on a smooth, non-absorbent surface by brush.
Drying Time	Surface Dry: 1 - 2 hrs.
@27 ± 2°C & RH 60 ± 5%	Recoating: Min. 8 hrs.
Gloss Levels / Sheen levels	Satin.
Thinning	Upto 30% by volume using Nerolac General Purpose Thinner.
Flash Point	Not below 30°C.
Stability of Thinned Paint	Use within 24 hrs.

**Actual coverage may vary depending on method & condition of application, surface roughness & shade.

PRECAUTIONS

- 01) Refer to the MSDS for "Nerolac Satin Enamel" for safety measures & precautions.
- 02) Store in well ambient conditions, ventilated locations & away from the source of ignition and fire.
- 03) Keep away from children.
- 04) In case of eye / skin contact wash with plenty of water.
- 05) Inhalation / Injection is dangerous. In either case, move to fresh air & consult medical practitioners.
- 06) Do not apply when ambient temperature might drop to level below 10°C within 4 hrs. of application.
- 07) New plaster should be allowed to cure for minimum 12 weeks.
- 08) Avoid extra thinning for better results.
- 09) Can be tinted with Nerolac Hi-Power Universal Stainer before thinning. Do not add more than 5% of Nerolac Hi-Power Universal Stainer. After tinting & before application, stir the tinted paint well.
- 10) The container must be tightly closed when not in use. Stir well and strain before use.
- 11) Use safety equipments like rubber or polythene gloves, safety goggles / glasses & face mask.

POST APPLICATION INSTRUCTIONS

For removing stains, sponge clean with a mild soap solution and wipe clean. Ensure a drying time of 1 week before cleaning.

SAFETY FEATURES

Flammable.

PACK SIZES

500 ml., 1 ltr., 4 ltrs., 10 ltrs., 20 ltrs.

SHADE RANGE

As per Standard Nerolac Enamel Shade Card and Color Scapes Fandeck.