

# Nerocoat Product Specifications – Epoxy Powders.

## Substrates

Aluminium  
Cold rolled Cold Annealed ( CRCA )Steel

## Surface Preparation

For normal applications – chemical cleaning and surface treatment.

For Aluminium – Chromatising.  
For Steel – Iron Phosphate / Low Wt. Zinc phosphate.

## Application Conditions

### Application Method:

Electrostatic Powder Spray  
- 40 to – 120 KV (Kilovolt)

### Film Thickness:

For normal usage 50 – 60 microns.

### Curing Schedule:

200°C for 10 to 15 minutes ( Object Temp.)

## Powder Characteristics

### Sieve Analysis:

( By Alpine Air Jet Sieve A 200 L.S.)

Below 32 microns	42 ± 3 %
Below 90 microns	> 99%
Below 125 micron	100 %.

### Specific Gravity:

1.4 – 1.8 ( Depending upon colour).

### Theoretical Coverage:

12 Sq.meters per Kg.  
At a typical specific gravity of 1.60, and at 50 microns dry film thickness assuming 100% application efficiency.

**Performance** will vary with colour,baking schedule, substrate type and thickness.

The following are typical performance properties when White or Off White Epoxy Powder Coatings are applied to chemically cleaned and surface treated light guage metal substrate. We suggest each proposed substrate be tested to confirm acceptability.

### Storage:

Product has shelf life of 6 months at 25°C and Relative Humidity of 50%. Cooler temperatures and lower humidity are recommended.

## Performance Properties

### Physical Tests:

Type	Pure Epoxy
Colour	In desired shades
Gloss @ 60°	Matt :5 – 20% S / G : 45 – 65% Glossy: > 90%
Finish	Available in Smooth, Texture and Structure finishes.
Hardness (Pencil)	H to 2H
Flexibility	Passes 6.25 mm
Adhesion (cross hatch tape test)	Excellent. GT-0 ( 1mm squares)
Impact (Direct / Reverse)	100 Kg.cm

### Accelerated Tests:

Humidity : 1000Hrs.  
No blisters or other failures.

5% Salt Spray : 750 Hrs.  
No face rust, 3mm creepage from scribe.  
( On CRCA steel, chemically treated)

Water Immrsion : 500Hrs. @ 49°C in Distilled water.  
No blistering or other changes.

## Typical Applications

### Chemical Resistance Tests:

Epoxy Powder Coatings are highly resistant to wide variety of solvents and chemicals.

Dielectric Applications, Wire Goods ( Baskets), Electrical Industry Switch Gears, Laboratory Furnitures, Machine Components, Battery Covers and Trays, etc.

The data given herein is meant to serve only as a guide to user. The customers are advised to evaluate the product for their end use. Kansai Nerolac Paints do not assume any responsibility with regard to accuracy or reproducibility of this data as the paint film performance largely depends upon surface preparation and application conditions which may vary from customer to customer and is beyond our control.