



NEROLAC
PAINT+

DESCRIPTION

Bluhm combines sandblasted effects with softer shades to bring the coastal paradise right to your home. Featuring a sandy finish reminiscent of the Mediterranean shores, it creates a warm and inviting ambience in any room.

PRODUCT FEATURES

- **Decorative Effect:** Metallic Sandblasted Effect
- **Luminous:** Light reflections
- **Single coat:** Instant decorative effect
- **Lead-free**
- **Very Low VOC**

APPLICATION PROCEDURE

SYSTEM	PRODUCT	DILUTION	APPLICATION TOOLS	NUMBERS OF COATS	DRYING TIME
Primer	Nerolac Premium Primer WT	50% by volume with water	Brush, Roller or Spray	1 coat	4-5 hours
Putty	Nerolac AcrylicWall Putty	No	Putty knife blade (Patra)	2 coats	4-5 hours
	OR				
	Nerolac Cement Putty	25-35% by weight with Water	Putty knife blade (Patra)	2 coats	4-5 hours
Primer/ Self-Priming	Nerolac Premium Primer WT	50% by volume with water	Brush + Roller, Spray, Felt roller	1 coat	4-5 hours
	OR				
	Kansai Select Texture Basecoat	50% by volume with water	Brush + Roller, Felt roller	1 coat	4-5 hours
Base Coat	Kansai Select Texture Basecoat	20-30% by volume with water	Brush + Roller, Felt roller	2 coats	4-5 hours
Top Coat	Kansai Select Bluhm	The product does not need to be diluted; it is ready to use.	Brush	1 coat	4-5 hours

BLUHM APPLICATION

- Apply Bluhm in the chosen shade with the help of a brush with circular hand movements.
- Post creating 2ft x 2ft patches smoothen it with zig-zag hand movements.
- Carry out this process without any interruptions or re-applications to prevent overlapping on previously decorated areas. Let it dry for 4-5 hours
- It is advisable to make a small test before executing the work. We also recommend mixing any different batches of product after colouring and before application.
- Kansai Nerolac Paints strongly recommends the use of its own **Kansai Select Texture Basecoat**, considering it to be the most suitable basecoat for enhancing both the aesthetic aspect and the compatibility of the products in the various application coats.
- In case this does not happen, Kansai Nerolac Paints is not responsible for any unsuccessful work.

TECHNICAL CHARACTERISTICS

PACKAGING	1 Ltr
COVERAGE	70-90 sq.ft/L/coat
SPECIFIC WEIGHT	1.3 - 1.5 Kg/Ltr
STORAGE AND WORKING TEMPERATURE	Min. + 7°C, Max. + 35°C
SHADE RANGE	Kansai Select Bluhm Catalogue
APPLICATION TOOLS	Brush
COUNTRY ORIGIN	ITALY
SHELF LIFE	2 Years
V.O.C. CONTENT	Less than 20 gm/Ltr
LEAD CONTENT	Lead content does not exceed 90 parts per million