



NEROLAC
PAINT+

DESCRIPTION

Nylum is a matt decorative product with natural warm wraparound colours that reproduces the intricate patterns of antique stone, adding a sense of history and sophistication to your interiors. Its natural warm colours with a shaded effect can be traced back to large mineral masses in nature.

PRODUCT FEATURES

- **Natural:** Natural raw and natural materials
- **Shades:** Effects with refined overlays
- **Vintage:** Decoration with classic effects
- **Lead-free**
- **Low VOC**

APPLICATION PROCEDURE

SYSTEM	PRODUCT	DILUTION	APPLICATION TOOLS	NUMBERS OF COATS	DRYING TIME
Primer	Nerolac Premium Primer WT	50% by volume with water	Brush, Roller or Spray	1 coat	4-5 hours
Putty	Nerolac Acrylic Wall Putty	No	Putty knife blade (Patra)	2 coats	4-5 hours
	OR				
	Nerolac Cement Putty	25-35% by weight with Water	Putty knife blade (Patra)	2 coats	4-5 hours
Primer/ Self-Priming	Nerolac Premium Primer WT	50% by volume with water	Brush + Roller, Spray, Felt roller	1 coat	4-5 hours
	OR				
	Kansai Select Texture Basecoat	50% by volume with water	Brush + Roller, Felt roller	1 coat	4-5 hours
Base Coat	Kansai Select Texture Basecoat	20-30% by volume with water	Brush + Roller, Felt roller	2 coats	4-5 hours
Designer Finish	Kansai Select Nylum	The product does not need to be diluted; it is ready to use.	Trowel	2 coats	4-5 hours

Kansai Select Texture Basecoat Application: Kansai Texture Basecoat needs to be tinted as per the shade selected from the Kansai Select Nylum catalogue and then thin 1 litre Kansai Texture Basecoat with 250-300 ml of clean water. Apply 2 coats using roller in an interval of 3-4 hours. Let it dry for 4-5 hours.

NYLUM APPLICATION

- Apply first coat of Nylum (chosen shade) using the trowel, by forming an angle of about 45°C between the tool and the wall, at the same time exert moderate pressure so that the colour and components that form the product can be well blended and distributed, thus creating the design and decoration on the wall.
- After the first coat is completely dry, follow the same application method for the second coat, taking care to proceed without interruptions and restarts, thus avoiding accumulations of material.
- It is advisable to make a small test before executing the work. We also recommend mixing any different batches of product after colouring and before application.
- Kansai Nerolac Paints strongly recommends the use of its own **Kansai Select Texture Basecoat**, considering it to be the most suitable basecoat for enhancing both the aesthetic aspect and the compatibility of the products in the various application coats.
- In case this does not happen, Kansai Nerolac Paints is not responsible for any unsuccessful work.

TECHNICAL CHARACTERISTICS

PACKAGING	1 Ltr
COVERAGE	1.00-1.05 Kg/Ltr
SPECIFIC WEIGHT	1.00 – 1.05a
STORAGE AND WORKING TEMPERATURE	Min. + 5°C, Max. + 35°Ca
SHADE RANGE	Kansai Select Nylum
APPLICATION TOOLS	Trowel
COUNTRY ORIGIN	ITALY
SHELF LIFE	2 Years
V.O.C. CONTENT	Less than 20 gm/Ltr
LEAD CONTENT	Lead content does not exceed 90 parts per million