

Nerotherm 250

Product Description

Heat resistant synthetic oleoresinous medium based two pack leafing aluminium paint.

Recommended Use

Nerotherm 250 is a air-drying heat-resistant paint incorporated with leafing aluminium pigment and a durable protective medium. It provides a brilliant metallic finish and has good heat resistance up to a temperature of 250 degree Celcius.

PHYSICAL PROPERTIES

Color	Aluminum
Finish	Lustrous
Temperature Resistance (Dry)	Max 250°C

Product Features

Excellent resistance to dry heat up to 250°C	Dual pack, air drying
Not Recommended in confined space & immersion Condition	Excellent adhesion to zinc silicate primer

Product Details

Volume solids



35 ± 2%

DFT/Coat



15 - 20 µ

VOC (EPA Method 24)



565 gm/Lit

Theoretical Coverage/Coat



17.5 – 23.3 m²/ltr.

Pack size

20 Ltr.: (17.40 Ltr. -Part A + 3.95 Kg Part B = 20 Ltr. Mix).

Drying at 30°C & 65% RH

Surface (Touch) Dry	1 – 3 Hrs.
Hard Dry	10 – 12 Hrs.
Full Cure	7 Days

Recoating Interval

Temperature	20°C	30°C	40°C
Min	16 Hrs.	10 Hrs.	6 Hrs.
Max	5 days	5 days	5 days

The drying time varies with respect to changes in temperature, humidity & DFT.

Nerotherm 250

Surface Preparation

Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SSPC SP 10 – Stainless steel, aluminium and other non-ferrous metals use non-metallic blast media like garnet. Remove sharp profile, without blank spots, remove dust & loose particles, then apply one coat of zinc silicate primer. The primer must be clean dry and free from moisture grease and other contaminants. Surface profile of max 10 micron is acceptable if applied as DTM.

Surface Cleanliness:

- Remove oil, grease and other contaminants by suitable cleaner as per SSPC SP-1
- Remove dust, blast media and loose particles
- Surface should be clean & dry before application of coating

Application Instructions

Stir the paint in the drum until homogenous. If settling is observed in drum, loosen the settled material & mix it with the help of pneumatic stirrer. Use Nerolac recommended thinner as specified.

Mixing Ratio by Weight

Component A : Component B	60 : 40
Pot Life	NA
Curing Mechanism	Solvent release and oxidative drying

Thinner Consumption

Air Assisted Spray	5 – 15%
Airless Spray	0 – 10%
Brush	0 – 10%

The product can be applied by:

- Airless Spray – Nozzle pressure: 175 bar [2500 psi] Nozzle orifice: 0.015"–0.017"
- Conventional Spray / Air Assisted Spray
- Brush

During application following precautions should be taken:

- Relative humidity must be below 85% during application as well as during curing
- Do not allow material to remain in hoses, gun or spray equipment
- Clean all equipment with recommended thinner immediately after completion of job

Environmental Conditions

Surface temperature must be 3°C above Dew Point to prevent condensation.

Air	5 – 40°C
Surface	5 – 50°C
Relative Humidity	< 85%

Storage & Shelf Life

12 months under normal storage condition in original sealed containers at 30°C

Heavy pigments will have a natural tendency to settle down over time. Mix uniformly with heavy duty stirrer prior to usage. Hard settling may occur if stored above the recommended storage temperature.

Nerotherm 250

Safety Precautions

Please refer to the Material Safety Data Sheet.

Product Compatibility

Compatible over Suitable Zinc Silicate Primer.

Special Notes

Thinner consumption may vary depending upon site conditions. Practical covering capacity depends on application techniques, ambient conditions, wastage, surface condition etc. The drying time and overcoating interval vary with respect to change in temperature, humidity, film thickness, ventilation, thinner intake etc.

DISCLAIMER:

KANSAI NEROLAC PAINTS Ltd. (KNPL) warrants that all products are free from any defects of manufacture and comply with the specification given in their respective technical data sheet. No warranty can be given as to the results of use because conditions of use, such as site conditions, surface preparations, workmanship, weather, structural issues and other factors are beyond the control of **NEROLAC**. Purchaser agrees to seek the advice of qualified professionals to carry out tests and take trials to determine the suitability of products for their intended purpose prior to full scale use of KNPL products and assumes all risks.

The company does not assume any liability for unsatisfactory results, arising from the use of our products. Purchaser's sole liability is limited to replacement of product or refund of the purchase price paid if any product proven defective. No other warranties express or implied, shall apply including any warranty of merchantability or fitness for particular purpose.

KNPL shall not be liable for any consequential damages arising from the use of our products for unsatisfactory results. The information supplied in this data sheet is based on our experience through extensive research and is given in good faith in order to help prospective users. We reserve the right to update the information provided in our technical data sheet at any time without prior notice within the scope of technical progress or new developments

Issue Date :- Oct 25